



10
Sugar Maple



11
Royal Forest



20
American Cherry



21
Praline



31
Barnwood



40
Warm Maple



41
Nutshell



50
Natural Teak



51
Aged Oak

DESIGN

Product Type:	Floating LVT
Gauge:	0.118" (3mm)
Wear Layer:	12mil/0.3mm
Finish:	UV-Cured Commercial Grade Urethane
Size:	6"x36" planks with 12"x36" Underlay
Anti-Microbial:	No
Installation:	Peel and Stick LVT with Floating Underlay
Recommended Adhesive:	None Required
Square Feet Per Carton:	24 sq ft/ctn (2.22 m ²)
Pieces Per Carton:	16 (plank), 8 (underlay) pcs/ctn
Pounds per carton:	46 lbs/ctn (20.86 kg/ctn)

PERFORMANCE

Construction:	Heat and Pressure Cured
Classification:	ASTM F-1700 - Class III, Type A - Smooth, Type B - Embossed
Smoke Density:	ASTM E662 - Passes - < 450
Impact Insulation Class:	59
Squareness:	ASTM F2055 -10 Passes - maximum 0.010 in. (0.25mm)
Size and Tolerance:	ASTM F2055 - Passes - at ±0.016 in./lin. Ft. (0.4 mm/305 mm)
Dimensional Stability:	ASTM F2199 - Passes - no greater than 0.020 in./lin. Ft. (0.51 mm/305 mm)
Thickness:	ASTM F386 - Passes - as specified ±0.005 in. (0.13 mm)
Flexibility:	ASTM F137 - Passes - 1 in. (25.4-mm mandrel, no crack or break)
Static Load:	2,500 PSI (pounds per square inch)
Residual Indentation:	ASTM F1914 - Passes - average less than 8%
Slip Resistance:	ADA Compliant - > 0.6
Resistance To Chemicals:	ASTM F925 - Passes - no change
Resistance To Heat:	ASTM F1514 - Passes - less than 8 ave., max
Resistance To Light:	ASTM F1515 - Passes - less than 8 ave., max
Critical Radiant Flux:	ASTM E648 - Passes - > 0.45 watts/cm ² , Class 1

SUSTAINABILITY

Rapidly Renewable Resource Content:	0%
Certification:	FloorScore® Certificate

SERVICE


Warranties:	Limited 10 Year Commercial
-------------	----------------------------



60
English Walnut



61
Coastal Dunes



70
Warm Timber



80
Atlas Cedar



90
Heritage Cedar